

# DirectPlastics

Unit 7, Portland Business Park  
Richmond Park Road  
Sheffield  
S13 8HS

Tel: 0114 2560889

Fax: 0114 2560809

Email: [sales@directplastics.co.uk](mailto:sales@directplastics.co.uk)

## Technical Properties for Acetal

	Norm	Unit i.e.	Value
<b><u>Physical Properties</u></b>			
Specific Gravity	ISO 1183	g/cm <sup>3</sup>	1.39
Water Absorption	DIN 53495	%	0.2
Chemical resistance	-	-	-
Maximum service temp	-	degrees C	110
Minimum service temp	-	degrees C	-50
<b><u>Mechanical Properties</u></b>			
Tensile strength at yeild	ISO 527	MPa	>65
Elongation at yeild	ISO 527	%	10
Tensile strength at break	ISO 527	MPa	>20
Elongation at break	ISO 527	%	31
Impact strength	ISO 179	kJ/m <sup>2</sup>	0.B.
Notch impact strength	ISO 179	kJ/m <sup>2</sup>	6
Ball indentation (Rockwell)	ISO 2039	MPa	135
Shore D	DIN 53505	-	85
Flexural strength	ISO 178	MPa	-
Modulus elasticity	ISO 527	MPa	2600
<b><u>Thermal Properties</u></b>			
Vicat softening temp	ISO 306	degrees C	150
Heat deflection Temp	ISO 75	degrees C	155
Coefficient of expansion	DIN 53752	K-1 x 10 <sup>-4</sup>	1.1
Thermal conduct at 20	DIN 52612	W/(mxK)	0.31
<b><u>Electrical Properties</u></b>			
Volume resistivity	VDE 0303	x cm	>10 13
Surface resistivity	VDE 0303	-	>10 13
Dielectric constant @ 1MHz	DIN 53483	-	3.8
Diel. loss factor @ 1 MHz	DIN 53483	-	0.005
Dielectric strength	VDE 0303	kV/mm	40
Tracking resistance	DIN 53480	-	CTI 600

## Better Plastics

Nylon – Acetal – Tufnol – PTFE – Perspex - Lexan  
Polypropylene - PVC - HDPE - PEEK

# DirectPlastics

Unit 7, Portland Business Park  
Richmond Park Road  
Sheffield  
S13 8HS

Tel: 0114 2560889

Fax: 0114 2560809

Email: [sales@directplastics.co.uk](mailto:sales@directplastics.co.uk)

## Additional Data

Bondability	-	-	0
Friction Coefficient	DIN 53375	-	0.35
Flamability	UL 94	-	HB

## Chemical properties

Acid resistance			+
Hydroxid resistance (dilute)			+
Hydrocarbonat resistance			+
CKW resistance			0
Aromatic resistance			+
Ketone resistance			+
Resistance to hot water			+

## Better Plastics

Nylon – Acetal – Tufnol – PTFE – Perspex - Lexan  
Polypropylene - PVC - HDPE - PEEK