

Delrin

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples. We reserve the right of technical alterations.

Properties	Unit	Test method DIN EN ISO / ASTM	
Mechanical			
Density	g/cm ³	527 / D 792	1.42
Tensile strength at yield	MPa	527 / D 638	70
Tensile strength at break	MPa	527 / D 638	
Elongation at break	%	527 / D 638	25
Modulus of elasticity in tension	MPa	527 / D 638	3000
Modulus of elasticity in flexure	MPa	178 / D 790	2620
Ball indentation hardness	MPa	2039 / 1	170
Impact strength	kJ/m ²	179 / D 256	no br.
Creep rupture strength after 1000 hrs with static load	MPa		40
Time yield limit for 1% elongation after 1000 hrs	MPa		13
Coefficient of friction against hardened and ground steel p = 0.05 N/mm ² , v = 0.6 m/s	-		0.34
Wear conditions as above	µm/km		4.6
Thermal			
Crystalline melting point	°C	DIN 53 736	175
Glass transition temperature	°C	DIN 53 736	-60
Heat distortion temperature			
Method A	°C	R 75	124
Method B	°C	R 75	170
Max. service temperature			
short term	°C		150
long term	°C		110
Coefficient of thermal conductivity	W/(m K)		0.31
Specific heat	J/(g K)		1.5
Coefficient of thermal expansion	10 ⁻⁵ /K	DIN 53 483 / D 696	10
Electrical			
Dielectric constant at 10 ⁵ Hz		DIN 53 483	3.7 ***
Dielectric loss factor at 10 ⁵ Hz		DIN 53 483	0.005***
Specific volume resistance	Ω cm	DIN 60093	>10 ¹⁴ ***
Surface resistance	Ω	DIN 60093	>10 ¹⁴ ***
Dielectric strength 1 mm	kV/mm	ASTM 149	>50 ***
Tracking resistance		53 480	KA 3c ***
Miscellaneous			
Moisture absorption: Equilibrium in standard atmosphere (23 °C / 50 % relative humidity)	%	62	<0.3
Water absorption at saturation at 23°C	%	62	0.5
Resistance to hot water, washing soda			not resistant
Flammability according to UL standard 94			HB
Resistance to weathering			Natural—not resistant Black - resistant

*** electrical values may be reduced for black material. Testing of part is recommended.